



	temp.	SEBS	SBS
Acetone	23°C	G	M
Acids up to 80%	23°C	E	M
Alcohol	23°C	E	G
Alkalis	23°C	E	G
Brake fluid	23°C	G	M
Chlorinated solvents	23°C	P	P
Diesel	23°C	P	P
Ethylene glycol	23°C	E	E
Petrol (gasoline)	23°C	P	P
Salt solution	23°C	E	G
Soda lye	23°C	E	M
Water – cold	23°C	E	G
Water – hot	96°C	G	P

E = Excellent
 G = Good
 M = Moderate
 P = Poor

Korrels BV

Stationsweg 16
 8191 AH WAPENVELD
 Tel. 0031 (0)38 447 9325
 Fax. 0031 (0)38 447 9320
 info@korreels.nl



The above properties are only a guideline and should be interpreted as standard typical information. We do not hold any responsibility. For specific information about the chemical resistance of your specific material please contact our offices.